

## PRODUCT DATA SHEET

# SikaBiresin® GC050 (GC1 050)

## EPOXY GELCOAT FOR STANDARD APPLICATIONS IN TOOLING – WHITE

### APPLICATIONS

- Manufacturing of gauges, negatives and foundry patterns

### MAIN PROPERTIES

- Good spreading and covering properties
- Good workability

### DESCRIPTION

Basis	Two component epoxy system
Component A	<b>SikaBiresin® GC050</b> , epoxy resin, filled, white
Component B	<b>SikaBiresin® GC11</b> , amine, unfilled, amber
Component B	<b>SikaBiresin® GC14</b> , amine, unfilled, amber

### PHYSICAL PROPERTIES

		Resin (A)	Hardener (B)	Hardener (B)
Components		<b>SikaBiresin® GC050</b>	<b>SikaBiresin® GC11</b>	<b>SikaBiresin® GC14</b>
Viscosity, 25 °C	mPa.s	~ 13,000	~ 1,400	~ 500
Density	g/cm <sup>3</sup>	1.59	1.08	1.03
Mixing ratio A:B	in parts by weight	100	10	10
Mixing ratio A:B	in parts by volume	100	15	15
		Mixture		
Colour		white		
Viscosity, 25 °C	mPa.s	~ 13,000		~ 9,000
Pot life, 25 °C, 165 g	min	~ 19		~ 35
Geltime, 23 °C	min	~ 60		~ 120
Tacky time, 23 °C	min	~ 60 – 120		~ 120 – 200

## MECHANICAL PROPERTIES

approx. values; values after post curing 24 h / 23 °C + 16 h / 50 °C

			SikaBiresin® GC11	SikaBiresin® GC14
Density, 23 °C	ISO 2781	g/cm <sup>3</sup>	1.57	1.56
Shore hardness	ISO 868	-	D 88	D 88
Flexural modulus	ISO 178	MPa	4,450	4,450
Flexural strength	ISO 178	MPa	72	66

## THERMAL AND SPECIFIC PROPERTIES

approx. values; values after post curing 24 h / 23 °C + 16 h / 50 °C

			SikaBiresin® GC11	SikaBiresin® GC14
Glass transition temperature	ISO 11359	°C		
- 48 h / 23 °C			50	53
- 16 h / 50 °C			75	77
- 16 h / 80 °C			85	77

## PACKAGING UNITS

▪ Resin (A), SikaBiresin® GC050	12 x 0.5 kg / 5 kg
▪ Hardener (B), SikaBiresin® GC11	0.5 kg / 12 x 0.05 kg / 1 kg
▪ Hardener (B), SikaBiresin® GC14	0.5 kg / 12 x 0.05 kg

## PROCESSING DATA

- The material, processing and mould temperature should be at least 18 – 25 °C.
- Component A must be stirred thoroughly before use.
- Recommended release agents are Sika® Liquid Wax-815 or Sika® Pasty Wax-818. For more information, see Product Data Sheets of the release agents.
- Pay attention to dry conditions and dry mould surfaces while processing.
- Porous surfaces have to be well sealed before.
- Both components have to be mixed thoroughly according to mixing ratio with a spatula or slow speed mixing equipment.
- Apply the gelcoat in a homogenous thickness on the mould by using a flat, short-haired brush. We recommend to apply the material in a uniform direction in order to get a homogeneous, even and void-free surface coat.
- Within the geltime of gelcoat we recommend to apply a coupling layer or other backfilling layer in order to avoid adhesion problems.
- In order to improve resistance of gelcoat and final part against temperature influences, solvents as well as exposition of water, a post curing process of the final part is recommended. In this case a slow increase and slow decrease of temperature is required.
- Further post curing of the demoulded part can improve the final mechanical properties.
- Depending on the geometry and weight of the part, it is recommended to use a conformer while post curing.
- For cleaning the final part from release agent residues, we recommend Sika® Reinigungsmittel-5. Before use of other cleaners, compatibility must be tested.

## STORAGE CONDITIONS

Shelf life	■ Resin (A), <b>SikaBiresin® GC050</b>	24 months
	■ Hardener (B), <b>SikaBiresin® GC11</b>	24 months
	■ Hardener (B), <b>SikaBiresin® GC14</b>	24 months
Storage temperature	■ Resin (A), <b>SikaBiresin® GC050</b>	15 – 25 °C
	■ Hardener (B), <b>SikaBiresin® GC11</b>	15 – 25 °C
	■ Hardener (B), <b>SikaBiresin® GC14</b>	15 – 25 °C
Opened packagings	■ Containers must be closed tightly immediately after use to prevent moisture ingress.	
	■ The residual material needs to be used up as soon as possible.	

### FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets

### BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

### LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

---

## Contact

---

**SIKA DEUTSCHLAND GMBH**  
Stuttgarter Straße 139  
72574 Bad Urach - GERMANY  
Phone: +49 7125 940 492  
Fax: +49 7125 940 401  
E-Mail: [tooling@de.sika.com](mailto:tooling@de.sika.com)  
Website: [www.sikaadvancedresins.de](http://www.sikaadvancedresins.de)

**SIKA AUTOMOTIVE FRANCE S.A.S.**  
ZI des Béthunes - 15, Rue de l'Equerre  
95310 Saint-Ouen-l'Aumône  
CS 40444  
95005 Cergy Pontoise Cedex - FRANCE  
Phone: +33 1 34 40 34 60  
Fax: +33 1 34 21 97 87  
E-Mail: [advanced.resins@fr.sika.com](mailto:advanced.resins@fr.sika.com)  
Website: [www.sikaadvancedresins.fr](http://www.sikaadvancedresins.fr)

**AXSON TECHNOLOGIES SPAIN, S.L.**  
C/Guardaagullés, 8 – P.I. Congost - 08520  
Les Franqueses del Valles (Barcelona) - SPAIN  
Phone: +34 93 225 16 20  
Fax: +34 93 225 03 05  
E-Mail: [spain@axson.com](mailto:spain@axson.com)  
Website: [www.sikaadvancedresins.es](http://www.sikaadvancedresins.es)

**AXSON ITALIA S.R.L.**  
Via Morandi 15  
21047 Saronno (Va) – ITALY  
Phone: +39 02 96 70 23 36  
Fax: +39 02 96 70 23 69  
E-Mail: [axson@axson.it](mailto:axson@axson.it)  
Website: [www.sikaadvancedresins.it](http://www.sikaadvancedresins.it)

**AXSON UK LTD**  
Unit 15 Studlands Park Ind. Estate  
Newmarket Suffolk, CB8 7AU - UNITED KINGDOM  
Phone: +44 1638 660 062  
Fax: +44 1638 665 078  
E-Mail: [sales.uk@axson.com](mailto:sales.uk@axson.com)  
Website: [www.sikaadvancedresins.uk](http://www.sikaadvancedresins.uk)

**SIKA AUTOMOTIVE SLOVAKIA S.R.O.**  
Tovarenska 49  
953 01 Zlate Moravce - SLOVAKIA  
Phone: +421 2 5727 29 33  
Fax: +421 37 3000 087  
E-Mail: [SikaAdvancedResins@sk.sika.com](mailto:SikaAdvancedResins@sk.sika.com)  
Website: [www.sikaadvancedresins.com](http://www.sikaadvancedresins.com)

**SIKA ADVANCED RESINS US**  
30800 Stephenson Highway  
Madison Heights, Michigan 48071 - USA  
Phone: +1 248 588 2270  
Fax: +1 248 616 7452  
E-Mail: [advanced.resins@us.sika.com](mailto:advanced.resins@us.sika.com)  
Website: [www.sikaadvancedresins.us](http://www.sikaadvancedresins.us)

**SIKA AUTOMOTIVE EATON RAPIDS, INC.**  
1611 Hults Drive  
Eaton Rapids, Michigan 48827 - USA  
Phone: +1 517 663 81 91  
Fax: +1 517 663 05 23  
E-Mail: [advanced.resins@us.sika.com](mailto:advanced.resins@us.sika.com)  
Website: [www.sikaadvancedresins.us](http://www.sikaadvancedresins.us)

**SIKA AUTOMOTIVE MEXICO S.A. DE C.V.**  
Ignacio Ramírez #20 Despacho 202 Col.  
Tabacalera C.P. 06030 CDMX - MEXICO  
Phone: +52 55 5264 49 22  
E-Mail: [marketing@axson.com.mx](mailto:marketing@axson.com.mx)  
Website: [www.sikaadvancedresins.mx](http://www.sikaadvancedresins.mx)

**SIKA AUTOMOTIVE SHANGHAI CO. LTD.**  
N°53 Tai Gu Road  
Wai Gao Qiao  
Free Trade Zone, Pudong  
200131 Shanghai - CHINA  
Phone: +86 21 58 68 30 37  
Fax: +86 21 58 68 26 01  
E-Mail: [marketing.china@axson.com](mailto:marketing.china@axson.com)  
Website: [www.sikaaxson.cn](http://www.sikaaxson.cn)

**Sika Ltd.**  
10 F, Shinagawa Intercity Tower B.  
2-15-2 Konan, Minato-ku  
Tokyo 108-6110 - JAPAN  
Phone: +81 3 6433 2314  
Fax: +81 3 6433 2102  
E-Mail: [advanced-resins@jp.sika.com](mailto:advanced-resins@jp.sika.com)  
Website: [www.jpn.sika.com](http://www.jpn.sika.com)

**AXSON INDIA PVT. LTD.**  
Office n°8, Building Symphony C - 3rd Floor  
Range Hills Road  
Bhosale Nagar  
Pune 411 020 - INDIA  
Phone: +91 20 25560 710  
Fax: +91 20 25560 712  
E-Mail: [info.india@axson.com](mailto:info.india@axson.com)  
Website: [www.sikaadvancedresins.in](http://www.sikaadvancedresins.in)